

Seamless and welded steel tubes

Dimensions and masses per unit length

English version of DIN EN 10220

DIN**EN 10220**

ICS 77.140.75

Supersedes DIN 2448 and
DIN 2458, February 1981 editions,
and DIN V ENV 10220, February
1994 edition.Nahtlose und geschweißte Stahlrohre – Allgemeine Tabellen
für Maße und längenbezogene Masse**European Standard EN 10220 : 2002 has the status of a DIN Standard.***A comma is used as the decimal marker.***National foreword**

This standard has been prepared by ECISS/TC 29 ‘Steel tubes and fittings for steel tubes’ (Secretariat: Italy). The responsible German body involved in its preparation was the *Normenausschuss Eisen und Stahl* (Steel and Iron Standards Committee), Technical Committee *Stahlrohre – Maße und Grenzabmaße*.

Amendments

DIN 2448 and DIN 2458, February 1981 editions, and DIN V ENV 10220, February 1994 edition, have been superseded by the specifications of EN 10220.

Previous editions

DIN 2448: 1981-02; DIN 2458: 1981-02; DIN V ENV 10220: 1994-02.

EN comprises 7 pages.

English version

Seamless and welded steel tubes

Dimensions and masses per unit length

Tubes lisses en acier, soudés et sans soudure – Tableaux généraux des dimensions et des masses linéiques

Nahtlose und geschweißte Stahlrohre – Allgemeine Tabellen für Maße und längenbezogene Masse

This European Standard was approved by CEN on 2002-10-16.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, the Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, the Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, and the United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Management Centre: rue de Stassart 36, B-1050 Brussels

Contents

	Page
Foreword.....	2
1 Scope	3
2 Normative references	3
3 Terms and definitions.....	3
4 Classification of outside diameters	3
5 Method of calculating masses per unit length.....	4
6 Dimensions and masses per unit length.....	4
Bibliography	7

Foreword

This document (EN 10220:2002) has been prepared by Technical Committee ECISS/TC 29, "Steel tubes and fittings for steel tubes", the Secretariat of which is held by UNI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2003, and conflicting national standards shall be withdrawn at the latest by June 2003.

When transforming the European Prestandard ENV 10220 into this European Standard EN 10220, ECISS/TC 29 regarded it as necessary to avoid any conflict with and to deviate as little as possible from ISO 4200:1991 because of the international trade in steel tubes and tubular products.

Table 1 of ENV 10220, which is identical with Table 2 of ISO 4200:1991, was therefore left unchanged for EN 10220.

Table 2 of EN 10220 contains dimensions for heavy wall tubes, that are not covered by ISO 4200:1991.

All parts of the European Standard series EN 10305 on steel tubes for precision applications contain tables with preferred dimensions, that are specific for the various parts of the standards series and the products and fields of application specified therein. Therefore, Table 3 from ENV 10220 with preferred dimensions for steel tubes for precision applications has become unnecessary, and has not been included in this standard.

This document supersedes ENV 10220:1993.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies, for seamless and welded circular steel tubes for general purposes (e. g. mechanical, pressure and structural applications), the following:

- preferred dimensions for outside diameter and wall thickness in millimetres and
- masses per unit length in kilogrammes per metre of plain end tube.

Technical Committees of ECISS and CEN should select these preferred dimensions for their product or functional standards, where appropriate.

The outside diameters are classified into three series reflecting the availability of accessories for piping systems (see Clause 4). This classification of outside diameters into different series and of preferred wall thicknesses indicates the range of steel tubes usually produced.

NOTE Information on dimensions for steel tubes for special applications can be found in other European Standards, e.g. prEN 10255, EN 10305 series, EN ISO 11960 and EN ISO 11961, information on dimensions for stainless steel tubes in EN ISO 1127.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

prEN 10266, *Steel tubes, fittings and structural hollow sections – Symbols and definition of terms for use in product standards*.

3 Terms and definitions

For the purpose of this European Standard the terms and definitions in prEN 10266 apply.

4 Classification of outside diameters

The outside diameters given in Tables 1 and 2 are classified into three series which may be described in the following way:

- series 1: outside diameters for which all the accessories needed for the construction of piping systems are standardized;
- series 2: outside diameters for which not all accessories are standardized;
- series 3: outside diameters for which very few standardized accessories exist.

NOTE 1 It is recommended to select, for tubes intended to be used as components of piping systems, outside diameters from series 1 in Table 1. Tubes with outside diameters in accordance with series 2 and 3 may not, or not easily, be available.

NOTE 2 Accessories for heavy wall tubes with dimensions in accordance with Table 2 may not be available regardless of the series in Table 1 to which the relevant outside diameter is allocated.

5 Method of calculating masses per unit length

The masses per unit length given in Tables 1 and 2 have been calculated from outside diameter D and wall thickness T to at least five significant figures, using the formula given below. They have been rounded to three significant figures for values of less than 100 and to the nearest whole number for larger values.

$$M = (D - T) \cdot T \times 0,0246615^1) \text{ kg/m}$$

where

M is the mass per unit length in kg/m,

D is the specified outside diameter in mm and

T is the specified wall thickness in mm.

The calculated values may also be applied to tubes with different density values, but have then to be multiplied by a factor of

- 1,015 for austenitic stainless steel²⁾
- 0,985 for ferritic and martensitic stainless steel³⁾.

NOTE EN 10088-1 provides distinguished density values for various groups of stainless steel grades which may be used for calculating purposes.

6 Dimensions and masses per unit length

Table 1 gives dimensions consisting of outside diameters D , from 3 series as described in Clause 4, and related wall thicknesses $T \leq 65$ mm and the calculated masses per unit length of plain end tube.

Table 2 gives dimensions consisting of outside diameters D and related wall thicknesses T from 70 mm to 100 mm and the calculated masses per unit length of plain end tube.

1) This factor is based on a density of 7,85 kg/dm³.

2) This factor is based on a density of 7,97 kg/dm³.

3) This factor is based on a density of 7,73 kg/dm³.

Table 1 – Dimensions (wall thicknesses $T \leq 65$ mm) and masses per unit length

Outside diameter <i>D</i> mm series	Wall thickness <i>T</i> , mm																						
	0,5	0,6	0,8	1	1,2	1,4	1,6	1,8	2	2,3	2,6	2,9	3,2	3,6	4	4,5	5	5,4	5,6	6,3			
	Mass per unit length, kg/m																						
10,2	0,120	0,142	0,185	0,227	0,266	0,304	0,339	0,373	0,404	0,448	0,487	0,651	0,694										
12	0,142	0,169	0,221	0,271	0,320	0,366	0,410	0,453	0,493	0,550	0,603	0,750											
12,7	0,150	0,179	0,235	0,289	0,340	0,390	0,438	0,484	0,528	0,590	0,648	0,701	0,750										
13,5	0,160	0,191	0,251	0,308	0,364	0,418	0,470	0,519	0,567	0,636	0,699	0,758	0,813	0,879									
14	0,166	0,198	0,260	0,321	0,379	0,435	0,489	0,542	0,592	0,664	0,731	0,794	0,852	0,923									
16	0,191	0,228	0,300	0,370	0,438	0,504	0,568	0,630	0,691	0,777	0,859	0,937	1,01	1,10	1,18								
17,2	0,206	0,246	0,324	0,400	0,474	0,546	0,616	0,684	0,750	0,845	0,936	1,02	1,10	1,21	1,3	1,41							
18	0,216	0,257	0,339	0,419	0,497	0,573	0,647	0,719	0,789	0,891	0,987	1,08	1,17	1,28	1,38	1,50							
19	0,228	0,272	0,359	0,444	0,527	0,608	0,687	0,764	0,838	0,947	1,05	1,15	1,25	1,37	1,48	1,61	1,73						
20	0,240	0,287	0,379	0,469	0,556	0,642	0,726	0,808	0,888	1,00	1,12	1,22	1,33	1,46	1,58	1,72	1,85						
21,3	0,256	0,306	0,404	0,501	0,595	0,687	0,777	0,866	0,952	1,08	1,20	1,32	1,43	1,57	1,71	1,86	2,01	2,12					
22	0,265	0,317	0,418	0,518	0,616	0,711	0,805	0,897	0,996	1,12	1,24	1,37	1,48	1,63	1,78	1,94	2,10	2,21					
25	0,302	0,361	0,477	0,592	0,704	0,815	0,923	1,03	1,13	1,29	1,44	1,58	1,72	1,91	2,07	2,28	2,47	2,61	2,68	2,91			
25,4	0,307	0,367	0,485	0,602	0,716	0,829	0,939	1,05	1,15	1,31	1,46	1,61	1,75	1,94	2,11	2,32	2,52	2,66	2,73	2,97			
26,9	0,326	0,389	0,515	0,639	0,761	0,880	0,998	1,11	1,23	1,40	1,56	1,72	1,87	2,07	2,26	2,49	2,70	2,86	2,94	3,20			
30	0,364	0,435	0,576	0,715	0,852	0,987	1,12	1,25	1,38	1,57	1,76	1,94	2,11	2,34	2,56	2,83	3,08	3,28	3,37	3,68			
31,8	0,386	0,462	0,612	0,760	0,906	1,05	1,19	1,33	1,47	1,67	1,87	2,07	2,26	2,50	2,74	3,03	3,30	3,52	3,62	3,96			
32	0,388	0,465	0,616	0,765	0,911	1,06	1,20	1,34	1,48	1,68	1,89	2,08	2,27	2,52	2,76	3,05	3,33	3,54	3,65	3,99			
33,7	0,409	0,490	0,649	0,808	0,962	1,12	1,27	1,42	1,56	1,78	1,99	2,20	2,41	2,67	2,95	3,24	3,54	3,77	3,88	4,26			
35	0,425	0,509	0,675	0,838	1,00	1,16	1,32	1,47	1,63	1,85	2,08	2,30	2,51	2,79	3,06	3,38	3,70	3,94	4,06	4,46			
38	0,462	0,553	0,734	0,912	1,09	1,26	1,44	1,61	1,78	2,02	2,27	2,51	2,75	3,05	3,35	3,72	4,07	4,34	4,47	4,93			
40	0,487	0,583	0,773	0,962	1,15	1,33	1,52	1,70	1,87	2,14	2,40	2,65	2,90	3,23	3,55	3,94	4,32	4,61	4,75	5,24			
42,4	0,517	0,619	0,821	1,02	1,22	1,42	1,61	1,80	1,99	2,27	2,55	2,82	3,09	3,44	3,79	4,21	4,61	4,93	5,08	5,61			
44,5	0,543	0,650	0,862	1,07	1,28	1,49	1,69	1,90	2,10	2,39	2,69	2,98	3,26	3,63	4,00	4,44	4,87	5,21	5,37	5,94			
48,3		0,706	0,937	1,17	1,39	1,62	1,84	2,06	2,28	2,61	2,93	3,25	3,56	3,97	4,37	4,86	5,34	5,71	5,90	6,53			
51		0,746	0,990	1,23	1,47	1,71	1,95	2,18	2,42	2,76	3,10	3,44	3,77	4,21	4,64	5,16	5,67	6,07	6,27	6,94			
54		0,790	1,05	1,31	1,56	1,82	2,07	2,32	2,56	2,93	3,30	3,65	4,01	4,47	4,93	5,49	6,04	5,47	6,68	7,41			
57		0,835	1,11	1,38	1,65	1,92	2,19	2,45	2,71	3,10	3,49	3,87	4,25	4,74	5,23	5,83	6,41	6,87	7,10	7,88			
60,3		0,883	1,17	1,46	1,75	2,03	2,32	2,60	2,88	3,29	3,70	4,11	4,51	5,03	5,55	6,19	6,82	7,31	7,55	8,39			
63,5		0,931	1,24	1,54	1,84	2,14	2,44	2,74	3,03	3,47	3,90	4,33	4,76	5,32	5,87	6,55	7,21	7,74	8,00	8,89			
70		1,37	1,70	2,04	2,37	2,70	3,03	3,35	3,84	4,32	4,80	5,27	5,99	6,51	7,27	8,01	8,60	8,89	9,90				
73		1,42	1,78	2,12	2,47	2,82	3,16	3,50	4,01	4,51	5,01	5,51	6,16	6,81	7,60	8,38	9,00	9,31	10,4				
76,1		1,49	1,85	2,22	2,58	2,94	3,30	3,65	4,19	4,71	5,24	5,75	6,44	7,11	7,95	8,77	9,42	9,74	10,8				
82,5		1,61	2,01	2,41	2,80	3,19	3,58	3,97	4,55	5,12	5,69	6,26	7,00	7,74	8,66	9,56	10,3	10,6	11,8				
88,9		1,74	2,17	2,60	3,02	3,44	3,87	4,29	4,91	5,53	6,15	6,76	7,57	8,34	9,37	10,3	11,1	11,5	12,8				
101,6						2,97	3,46	3,95	4,43	4,91	5,63	6,35	7,06	7,77	8,70	9,63	10,8	11,9	12,8	13,3	14,8		
108						3,16	3,68	4,20	4,71	5,23	6,00	6,76	7,52	8,27	9,27	10,3	11,5	12,7	13,7	14,1	15,8		
114,3						3,35	3,90	4,45	4,99	5,54	6,35	7,16	7,97	8,77	9,83	10,9	12,2	13,5	14,5	15,0	16,8		
127								4,95	5,56	6,17	7,07	7,98	8,88	9,77	10,0	11,0	12,1	13,6	15,0	16,8	18,8		
133								5,18	5,82	6,46	7,41	8,36	9,30	10,2	11,5	12,7	14,3	15,8	17,0	17,6	19,7		
139,7								5,45	6,12	6,79	7,79	8,79	9,78	10,8	12,1	13,4	15,0	16,6	17,9	18,5	20,7		
141,3								5,51	6,19	6,87	7,88	8,89	9,90	10,9	12,2	13,5	15,2	16,8	18,1	18,7	21,0		
152,4								5,95	6,69	7,42	8,51	9,61	10,7	11,8	13,2	14,6	16,4	18,2	19,6	20,3	22,7		
159								6,21	6,98	7,74	8,89	10,0	11,2	12,3	13,8	15,3	17,1	19,0	20,5	21,2	23,7		
168,3								6,58	7,39	8,20	9,42	10,6	11,8	13,0	14,6	16,2	18,2	20,1	21,7	22,5	25,2		
177,8								7,81	8,67	9,95	11,2	12,5	13,8	15,5	17,1	19,2	21,3	23,0	23,8	26,6			
193,7								8,52	9,46	10,9	12,3	13,6	15,0	16,9	18,7	21,0	23,3	25,1	26,0	29,1			
219,1								9,65	10,7	12,3	13,9	15,5	17,0	19,1	21,2	23,8	26,4	28,5	29,5	33,1	37,0		
244,5									12,0	13,7	15,5	17,3	19,0	21,4	23,7	26,6	29,5	31,8	33,0	37,0			
273									13,4	15,4	17,3	19,3	21,3	23,9	26,5	29,8	33,0	35,6	36,9	41,4			
323,9														47,9	53,8	59,8	67,2	74,6	80,5	83,5	93,8		
355,6														64,7	72,7	80,8	87,2	90,4	102				
406,4														69,7	78,4	87,1	94,0	97,4	109				
457														74,8	84,1	93,3	101	104	117				
508														79,8	89,7	99,6	108	112	125				
559														84,8	95,4	106	114	119	133				
610														89,8	101	112	125	135	140	157			
660														99,8	112	125	135	140	157				
711																							

Table 1 (continued)

Outside diameter <i>D</i> mm series	Wall thickness <i>T</i> , mm																						
	7,1	8	8,8	10	11	12,5	14,2	16	17,5	20	22,2	25	28	30	32	36	40	45	50	55	60	65	
	1	2	3	Mass per unit length, kg/m																			
10,2																							
	12																						
	12,7																						
13,5		14																					
	16																						
17,2		18																					
	19																						
20																							
21,3		22																					
	25		25,4																				
26,9		3,47	3,73																				
	30	4,01	4,34																				
31,8		4,32	4,70																				
	32	4,36	4,74																				
33,7		4,66	5,07	5,40																			
	35	4,89	5,33	5,69																			
38		5,41	5,92	6,34	6,91																		
40		5,76	6,31	6,77	7,40																		
42,4		6,18	6,79	7,29	7,99																		
	44,5	6,55	7,20	7,75	8,51	9,09	9,86																
48,3		7,21	7,95	8,57	9,45	10,1	11,0																
51		7,69	8,48	9,16	10,1	10,9	11,9																
	54	8,21	9,08	9,81	10,9	11,7	12,8	13,9															
57		8,74	9,67	10,5	11,6	12,5	13,7	15,0															
60,3		9,32	10,3	11,2	12,4	13,4	14,7	16,1	17,5														
63,5		9,88	10,9	11,9	13,2	14,2	15,7	17,3	18,7														
70		11,0	12,2	13,3	14,8	16,0	17,7	19,5	21,3	22,7													
	73	11,5	12,8	13,9	15,5	16,8	18,7	20,6	22,5	24,0													
76,1		12,1	13,4	14,6	16,3	17,7	19,6	21,7	23,7	25,3	27,7												
82,5		13,2	14,7	16,0	17,9	19,4	21,6	23,9	26,2	28,1	30,8	33,0											
88,9		14,3	16,0	17,4	19,5	21,1	23,6	26,2	28,8	30,8	34,0	36,5	39,4										
101,6		16,5	18,5	20,1	22,6	24,6	27,5	30,6	33,8	36,3	40,2	43,5	47,2	50,8									
114,3		108	17,7	19,7	21,5	24,2	26,3	29,4	32,8	36,3	39,1	43,4	47,0	51,2	55,2	57,7							
	18,8	21,0	22,9	25,7	28,0	31,4	35,1	38,8	41,8	46,5	50,4	55,1	59,6	62,4	64,9								
127		21,0	23,5	25,7	28,9	31,5	35,3	39,5	43,8	47,3	52,8	57,4	62,9	68,4	71,8	75,0	80,8						
133		22,0	24,7	27,0	30,3	33,1	37,1	41,6	46,2	49,8	55,7	60,7	66,6	72,5	76,2	79,7	86,1	91,7					
139,7		23,2	26,0	26,4	32,0	34,9	39,2	43,9	48,8	52,7	59,0	64,3	70,7	77,1	81,2	85,0	92,1	98,4					
141,3		23,5	26,3	26,8	32,4	35,3	39,7	44,5	49,4	53,4	59,8	65,2	71,7	78,2	82,3	86,3	93,5	99,9					
152,4		25,4	28,5	31,2	35,1	38,4	43,1	48,4	53,8	58,2	65,3	71,3	78,5	85,9	90,6	95,0	103	111	119				
159		26,6	29,8	32,6	36,7	40,1	45,2	50,7	56,4	61,1	68,6	74,9	82,6	90,5	95,4	100	109	117	127				
168,3		28,2	31,6	34,6	39,0	42,7	48,0	54,0	60,1	65,1	73,1	80,0	88,3	96,9	102	108	117	127	137	146			
177,8		29,9	33,5	36,7	41,4	45,2	51,0	57,3	63,8	69,2	77,8	85,2	94,2	103	109	115	126	136	147	158	167		
193,7		32,7	36,6	40,1	45,3	49,6	55,9	62,9	70,1	76,0	85,7	93,9	104	114	121	128	140	152	165	177	188	198	
219,1		37,1	41,6	45,6	51,6	56,5	63,7	71,8	80,1	87,0	96,2	108	120	132	140	148	163	177	193	209	223	247	
	244,5	41,6	46,7	51,2	57,8	63,3	71,5	80,6	90,2	98,0	111	122	135	149	159	168	185	202	221	240	257	273	288
273		46,6	52,3	57,3	64,9	71,1	80,3	90,6	101	110	125	137	153	169	180	190	210	230	253	275	296	315	333
323,9		55,5	62,3	68,4	77,4	84,9	96,0	108	121	132	150	165	184	204	217	230	256	280	310	338	365	390	415
355,6		61,0	68,6	75,3	85,2	93,5	106	120	134	146	166	183	204	226	241	255	284	311	345	377	408	437	466
406,4		69,9	78,6	86,3	97,8	107	121	137	154	168	191	210	235	261	278	295	329	361	401	439	477	513	547
457		78,8	88,6	97,3	110	121	137	155	174	190	216	238	266	296	316	335	374	411	457	502	545	587	628
508		87,7	98,6	108	123	135	153	173	194	212	241	266	298	321	354	376	419	462	514	565	614	663	710
	559	96,6	109	119	135	149	168	191	214	234	266	294	329	367	391	416	464	512	570	628	684	738	792
610		106	119	130	148	162	184	209	234	256	291	322	361	402	429	456	510	562	627	691	753	814	874
	660	114	129	141	160	176	200	226	254	277	316	349	392	436	466	496	554	612	683	752	821	888	954
711		123	139	152	173	190	215	244	274	299	341	377	423	472	504	536	599	662	739	815	890	963	1036
	762	132	149	163	185	204	231	262	294	321	366	405	454	507	542	576	645	712	796	878	959	1039	1117
813		141	159	175	198	218	247	280	314	343	391	433	486	542	579	616	690	763	852	941	1028	1114	1199
	864	150	169	186	211	231	262	298	335	365	416	461	517	577	617	657	735	813	909	1004	1097	1190	1281
914		159	179	196	223	245	278	315	354	387	441	488	548	612	654	696	780	862	964	1065	1165	1264	1361
1016		177	199	219	248	273	309	351	395	431	491	544	611	682	729	777	870	963	1078	1191	1303	1415	1524
1067		186	209	230	261	286	325	369	415	453	516	572	642	717	767	817	915	1013	1134	1254	1373	1490	1606
1118		195	219	241	273	300	341	387	435	475	542	600	674	753	805	857	961	1063	1191	1317	1442	1556	1688
	1168	203	229	252	286	314	356	404	455	497	566	627	705	787	842	896	1005	1113	1246	1379	1510	1639	1768
1219		212	239	263	298	328	372	422	475	519	591	655	736	822	880	937	1050	1163	1303	1441	1579	1715	1850
1321		230	259	285	323	355	403	458	515	563	642	711	799	893	955</								

Table 2 – Dimensions (wall thicknesses $70 \text{ mm} \leq T \leq 100 \text{ mm}$) and masses per unit length

Outside Diameter <i>D</i> mm	Wall thickness <i>T</i> , mm			
	70	80	90	100
	Mass per unit length kg/m			
219,1	257			
244,5	301	325		
273	350	381		
323,9	438	481	519	552
355,6	493	544	590	630
406,4	581	644	702	765
457	668	744	815	880
508	756	844	928	1006
559	844	945	1041	1132
610	932	1046	1154	1258
660	1019	1144	1265	1381
711	1107	1245	1378	1507

Bibliography

EN 10088-1, *Stainless steels – Part 1: List of stainless steels*.

prEN 10255, *Non-alloy steel tubes suitable for welding or threading – Technical delivery conditions*.

EN 10305-1, *Steel tubes for precision applications – Technical delivery conditions - Part 1: Seamless cold drawn tubes*.

EN 10305-2, *Steel tubes for precision applications – Technical delivery conditions - Part 2: Welded cold drawn tubes*.

EN 10305-3, *Steel tubes for precision applications – Technical delivery conditions - Part 3: Welded cold sized tubes*.

prEN 10305-4, *Steel tubes for precision applications – Technical delivery conditions - Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems*.

prEN 10305-5, *Steel tubes for precision applications – Technical delivery conditions - Part 5. Welded and cold sized square and rectangular tubes*.

prEN 10305-6, *Steel tubes for precision applications – Technical delivery conditions - Part 6: Welded cold drawn tubes for hydraulic and pneumatic power systems*.

EN ISO 1127, *Stainless steel tubes - Dimensions, tolerances and conventional masses per unit length (ISO 1127:1992)*.

EN ISO 11960, *Petroleum and natural gas industries – Steel pipes for use as casing or tubing for wells (ISO 11960:2001)*

EN ISO 11961, *Petroleum and natural gas industries – Steel pipes for use as drill pipe – Specification (ISO 11961:1996)*.

ISO 4200:1991, *Plain end steel tubes, welded and seemless – General tables of dimensions and masses per unit length*.